

# 240 Natural

## REINFORCED WATER-ACTIVATED TAPE

### DESCRIPTION

3-way fiberglass reinforced natural kraft carton sealing tape, manufactured with water-activated adhesive.

### PRODUCT APPLICATION

Used for two strip sealing cartons top and bottom. Works well on recycled cartons, and non-unitized loads. Recommended for use on light weight to average cartons up to 30 pounds.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA  
Customer Service: 800.IPG.8273 | 800.474.8273  
Tape Technical Service: 877.447.4832  
[www.itape.com](http://www.itape.com) | [info@itape.com](mailto:info@itape.com)

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 12/12

## INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

### CONSTRUCTION (PER 3,000 SQUARE FEET):

|                                |   |
|--------------------------------|---|
| <b>Top Ply:</b>                | 23 lb Natural Kraft Paper (virgin fibers)                                     |
| <b>Bottom Ply:</b>             | 23 lb Natural Kraft Paper (virgin fibers)                                     |
| <b>Laminating Adhesive:</b>    | 14.0 lb High Melt Index Polypropylene Based Co-Polymer                        |
| <b>Remoistenable Adhesive:</b> | 15 lb Chemically Grafted Starch Based Copolymer Adhesive, Designated as S3911 |
| <b>MD Reinforcement:</b>       | 2.82 lb (1-1-1-1-1) 75 Fiberglass (per 72mm), 1/2" spacing                    |
| <b>CD Reinforcement:</b>       | 1.34 lb (1-1-1) 150 Fiberglass, 1.20" spacing, 37 degree angle                |
| <b>Total Basis Weight:</b>     | 79.2 lb   |
| <b>PHYSICAL PROPERTIES:</b>    |   |
| <b>Caliper (mils):</b>         | 6.3   |
| <b>MD Tensile (lbs/in):</b>    | 74  |
| <b>CD Tensile (lbs/in):</b>    | 26  |

### ADHESION (WATER AT RECOMMENDED 110°F):

|                   |    |
|-------------------|----|
| <b>Fipago:</b>    |    |
| 2/0               | 49 |
| 2/1               | 71 |
| 5/0               | 75 |
| 15/0              | 90 |
| <b>McClaurin:</b> | 86 |



**CENTRAL**  
brand

# 240 Snowwhite

## REINFORCED WATER-ACTIVATED TAPE

### DESCRIPTION

3-way fiberglass reinforced snow white carton sealing tape, manufactured with water-activated adhesive.

### PRODUCT APPLICATION

Used for two strip sealing cartons top and bottom. Works well on recycled cartons, and non-unitized loads. Recommended for use on light weight to average cartons up to 25 pounds.



intertape polymer group™

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 12/12

## INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

### CONSTRUCTION (PER 3,000 SQUARE FEET):

|                                |  |
|--------------------------------|--|
| <b>Top Ply:</b>                | 25 lb. White Paper (virgin fibers)   |
| <b>Bottom Ply:</b>             | 23 lb. Natural Kraft Paper (virgin fibers)                                     |
| <b>Laminating Adhesive:</b>    | 14 lb. High Melt Index Polypropylene Based Co-Polymer                          |
| <b>Remoistenable Adhesive:</b> | 15 lb. Chemically Grafted Starch Based Copolymer Adhesive, Designated as S3911 |
| <b>MD Reinforcement:</b>       | 2.82 lb. (1-1-1-1) 75 Fiberglass (per 72mm), ½" spacing                        |
| <b>CD Reinforcement:</b>       | 1.34 lb. (1-1-1) 150 Fiberglass, 1.20" spacing, 37 degree angle                |
| <b>Total Basis Weight:</b>     | 81.2 lb.   |

### PHYSICAL PROPERTIES:

|                               |     |
|-------------------------------|-----|
| <b>Caliper</b> (mils):        | 6.4 |
| <b>MD Tensile</b> (lbs./in.): | 68  |
| <b>CD Tensile</b> (lbs./in.): | 25  |

### ADHESION (WATER AT RECOMMENDED 110°F):

|                   |    |
|-------------------|----|
| <b>Fipago:</b>    |    |
| 2/0               | 42 |
| 2/1               | 73 |
| 5/0               | 66 |
| 15/0              | 84 |
| <b>McClaurin:</b> | 90 |



**CENTRAL**  
brand