





Good පිමර්ර්මර Best Superior



Brush Step® features a lighter-weight double rib high/low design that performs the scraping function of the mat. The ribbed surface brushes, channels, and conceals dirt and debris and is the perfect choice for light to medium traffic areas.

<u>Test</u>	Test Description	* <u>Results</u>
Abrasion Resistance ASTM D3884-01	Test specimen is subjected to the rubbing action of two abrading wheels under controlled conditions. Results measured in Weight loss (Grams)	1.15
Accelerated Wear	Test specimen is subjected to the action of rollers under a specified load. Sample is rotated 10° after each pass. Results measured in thickness loss (%)	38.66%
Accelerated Soiling ASTM D6540-00	Test specimen is subjected to an accelerated soiling process. for a predetermined length of time. The sample is vacuumed, rated, submitted to an extraction device, then rated again.	(Based on visual inspection) 4.0 - Vacuum Rating 4.5 - Rating After Extraction
Water Retention	Test specimen is submerged in water for 5 minutes, removed, drained for 15 seconds and weighed. Results measured in weight gain. (Gallons per sq. yd.)	.25
Flammability ASTM D2859 (CPSC FF 1-70)	Intended to measure the mattings response to an ignition source in a controlled environment. The uncharred area of the test specimen must be greater than 1 inch to pass.	3.5 Inches

^{*}All testing of NoTrax® floor matting has been performed by an independent testing laboratory.

AATCC Rating Key (For Accelerated Soiling Test)		
5 4 3 2 1	No change Slight change Noticeable change Considerable change Severe change	

• Face Weight: 19 oz. per sq. yd.

• Thickness: 3/8"

• Weight: .77 lbs sq./ft.

• Vinyl Backing reduces mat movement

• Backing Thickness: 70 +/- 4 Mils

• Stock Sizes: 2' x 3', 3' x 4', 3' x 5', 3' x 6', 3' x 10',

4' x 6', 4' x 8'

• Roll Sizes: 3' x 60', 4' x 60', 6' x 60'

• Custom Sizes available in 3', 4', and 6' widths



